

NICKEL ALLOY

K500 - 2.4375



K500 - 2.4375

Nickel Alloy K500, also known as 2.4375 or Monel K500, is a nickel-copper alloy that can be age-hardened by adding aluminum and titanium. It is known for its resistance to corrosion and its ability to maintain good mechanical properties in challenging environments, especially in marine and chemical environments, and high strength at elevated temperatures.

KEY FEATURES

- Excellent corrosion resistance
- High strength
- Non-magnetic
- Good ductility and toughness
- Low magnetic permeability

CHEMICAL PROPERTIES

Nickel (Ni)	Copper (Cu)	Aluminium (Al)	Iron (Fe)	Manganese (Mn)	Silicone (Si)	Titanium (Ti)	Carbon (C)	Sulphur (S)
63%	27-33%	2.3-3.2%	2%	1.5%	0.5%	0.35-0.85%	0.25%	0.1%

MECHANICAL PROPERTIES

Tensile strength (N/mm ²)	1100
Yield strength (N/mm ²)	790
Elongation (% in 4D)	20
Hardness - Rockwell (HRB) max	75-85
Hardness - Brinell (HB) max	315

PHYSICAL PROPERTIES

Density (kg/m ³)	8440	
Modulus of elasticity (Gpa)	179	
Mean coefficient of thermal expansion	0-100°C (µm/m/°C)	13.4
	0-350°C (µm/m/°C)	13.9
	0-538°C (µm/m/°C)	14.5
Thermal conductivity	at 100°C (W/m.K)	17.2
	at 500°C (W/m.K)	20.1
Specific Heat 0-100°C (J/kg.K)	418	
Electrical resistivity (nΩ.m)	242	
Melting point (°C)	1350	

MARKET SECTORS



Oil & Gas Industry

Downhole equipment, pump shafts, valve stems, tubing



Chemical Processing

Reactors, vessels, heat exchangers, piping systems



Marine Equipment

Marine shafts, valves, fasteners, pump and valve components



Electrical Industry

Electrical connectors, springs, switchgear components



Aerospace Industry

Fasteners, springs, parts, missile systems, fuel tanks



Power Generation

Turbine components, blades, boiler feedwater systems